

Martinswerk GmbH
Kölner Straße 110
D-50127 Bergheim
phone: +49-2271-902-0
e-mail: hubermaterials@huber.com

HN-336

Alumina Trihydrate

DESCRIPTION

HN-336 is a halogen-free, medium particle size ATH product that provides low cost flame retardant and smoke suppression in a variety of applications. The particle size distribution is specifically designed for low viscosity, high filler loading levels, and excellent processing characteristics, up to 200°C.

APPLICATIONS

HN-336 is recommended for spray-up or hand-lay up FRP applications, filament winding, panel production, resin injection, foam materials, cast polymer and epoxy parts, coatings, adhesives, latex, vinyl and urethane compounds.

PHYSICAL FORM: White powder
GENERIC TYPE: Alumina trihydrate

MORPHOLOGY: Hexagonal Platelets
CAS No.: 21645-51-2

TYPICAL CHEMICAL ANALYSIS

Al(OH) ₃ , %	99.6
SiO ₂ , %	<0.04
Fe ₂ O ₃ , %	<0.02
Na ₂ O (total), %	0.2
Na ₂ O (soluble), %	0.02
Free Moisture (TGA), 105° C, %	0.22

TYPICAL PHYSICAL PROPERTIES

Screen Analysis	
% < 45 micron	80
% < 10 micron	40
% < 1 micron	5
Median Particle Diameter, microns	14
Loss on ignition, 550° C, %	34.5
Surface Area BET (m ² /gm)	1.7
Specific Gravity (gm/cm ³)	2.42
Bulk Density- packed (gm/lit.)	1270
Brightness Ry	94
CIELAB, L*	97
Moh's Hardness	3.0
Electrical Conductivity, µS/cm	<130
Oil Absorption, ml/100gm	21

PACKAGING & STORAGE

25 kg paper bag, 1000 kg pallet

The product should be stored under dry and clean conditions in its original packing. The moisture content may increase if not stored under dry conditions.

©2022 J.M. Huber Corporation. Huber and the Huber logo are registered trademarks of J.M. Huber Corporation.

THERE ARE NO IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Refer to Huber's Standard Conditions of Sale for the only express warranties applicable to the Huber products. Products incorporating Huber products are not warranted by Huber. In no event is Huber liable for consequential damages.

Revised 12/11