



MAGNIFIN[®] H-5 MV

Magnesium hydroxide

Einsatzbeispiele / Applications

MAGNIFIN H-5 MV ist ein hochreines Magnesiumhydroxid mit hoher Schüttdichte, das einer speziellen chemischen Oberflächenbehandlung unterzogen wurde. Die mineralische Rohstoffbasis sowie ein patentierter Prozess garantieren einen gleichmäßigen Kristallaufbau.

MAGNIFIN H-5 MV wird empfohlen für die halogenfreie, flammwidrige und rauchunterdrückende Ausrüstung von thermoplastischen oder vernetzten Kunststoffen, speziell polyolefinische Compounds sowie für Kautschukmischungen. Die Wirkung basiert auf einer thermischen Zersetzung, die erst bei 340°C beginnt. Dabei entstehen keine toxischen oder korrosiven Gase. Die Oberflächenbehandlung unterstützt die Verträglichkeit des Füllstoffes mit der Polymermatrix und verbessert die Verarbeitbarkeit sowie die mechanischen Eigenschaften des Compounds.

MAGNIFIN H-5 MV is a high-purity magnesium hydroxide modified with a proprietary surface treatment. Based on a mineral raw material, the patented process guarantees a regular structure of the crystallite.

MAGNIFIN H-5 MV represents a halogen free flame retardant with low smoke emission and high thermal stability up to 340°C. It is recommended for thermoplastic or crosslinked polyolefins and rubber compounds. During decomposition, no toxic or corrosive gases are generated. The surface treatment favours the compatibility between filler and polymer matrix. Processing, mechanical and electrical properties, also flame retardancy in many applications, can be improved.

Durchschnittsanalyse / Typical analysis

Mg(OH) ₂		[%]	≥ 99.8	(*)
Feuchte / Moisture (105 °C)		[%]	≤ 0.3	
				(bei Absackung / when packed)
Spezifische Oberfläche / Specific Surface Area (BET)		[m ² /g]	2.0 – 5.0	
Elektrische Leitfähigkeit / Electrical Conductivity		[µS/cm]	≤ 150	
				(10 % Susp. in deion. Wasser / 10 % susp. in de-ion water)
Teilchengröße / Particle Size	d ₁₀ [µm]	0.7 – 1.0	} gemessen mit MALVERN MASTERSIZER 2000 (Laserbeugung) } measured by MALVERN MASTERSIZER 2000 (laser diffraction)	
	d ₅₀ [µm]	1.6 – 2.0		
	d ₉₀ [µm]	2.4 – 4.4		
Siebrückstand > 45 µm / Sieve Residue > 45 µm [%]			≤ 0.1	
Schüttdichte / Bulk Density		[g/l]	450 – 600	

Typische Werte / Typical Data

Glühverlust / Loss on Ignition 1200°C	[%]	31	(*)
Dichte / Density	[g/cm ³]	2.4	(*)
Mohssche Härte / Mohs Hardness		2.5	(*)
Brechungsindex / Refraction Index		1.56 – 1.58	(*)
Weißgrad / Whiteness (DR LANGE 457 nm)	[%]	> 96	(*)

Al ₂ O ₃	[ppm] < 50	} Bestimmung mittels XRF an MAGNIFIN H-5 measured by XRF on MAGNIFIN H-5
Fe ₂ O ₃	[ppm] < 50	
MnO	[ppm] < 10	
CaO	[ppm] < 50	
NiO	[ppm] < 50	
Cr ₂ O ₃	[ppm] < 10	
B ₂ O ₃	[ppm] < 1	
Cu	[ppm] < 10	

(*) Werte mit einem Sternchen versehen, beziehen sich auf das unbeschichtete Substrat.

(*) Values with an asterisk refer to the uncoated substrate.

Die oben genannten Werte sind nur als Richtwerte zu verstehen und nicht etwa als zugesicherte Eigenschaften.
The above mentioned values should be taken only as indications and not as guaranteed properties.

Shipping Information

Packaging and minimum order quantity information is available from sales or customer service.

Safety and Handling Information

For specific safety, toxicity and handling information, please refer to the material safety data sheet on this product.

Chemical Registration Numbers

Chem. Bezeichnung / Chem. name:	Magnesium hydroxide
Formel / formula:	Mg(OH) ₂
CAS No.:	1309-42-8
EC/EINECS No.:	215-170-3

EUROPE, MIDDLE EAST, AFRICA

Martinswerk GmbH
Kölner Straße 110
D-50127 Bergheim

Phone: +49-2271-902-0
Fax: +49-2271-902-710

AMERICAS

Huber Engineered Materials
3100 Cumberland Boulevard
Suite 600
Atlanta, Georgia 30339

Phone: +1 (678) 247-7300
Fax: +1 (678) 247-2797

ASIA PACIFIC

Huber Fire Retardant Additives
(Qingdao) Co.Ltd
8th Floor No.2 Building, No.7,
Wuyishan Road, Huangdao District,
Qingdao – China

Phone: +86 532-58792008
Fax: +86 532-58792008

Web: www.martinswerk.de
www.hubermaterials.com

Email: info@martinswerk.com
hubermaterials@huber.com



THERE ARE NO IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Refer to Martinswerk's Standard Conditions of Sale for the only express warranties applicable to the Martinswerk products. Products incorporating Martinswerk products are not warranted by Martinswerk. In no event is Martinswerk liable for consequential damages. **MAGNIFIN**® is used, applied for, or registered as a trademark of MAGNIFIN Magnesiaprodukte GmbH & Co KG in various countries around the world.
© September 2022 Martinswerk GmbH